

Quantities and mixing ratios Technovit 5000 (without specimen)

mixing ratio	Powder	Liquid
20 g powder with 13 g liquid	63 %	37 %
25 g powder with 16 ml liquid		

*Kulzer embedding moulds. The stated mixing ratios are base values and can be varied slightly, depending on the application needs.